

## Technical Data Sheet

# **Protac™ Scribe**



#### **Product Description**

Protac<sup>™</sup> Scribe is a 40µ (1.6 mil) gloss finish biaxally-oriented polypropylene laminating film coated on one side with a pressure sensitive, aqueous acrylic adhesive, which is protected by a bleached Kraft release paper coated on one side with a siliconised polyethylene. Available in various sizes.

#### **Applications**

Protac<sup>™</sup> Scribe is ideally suited for application to heat-sensitive output and high ink coverage prints printed on photo gloss paper. The nature of this polypropylene on the Protac<sup>™</sup> Scribe makes it ideal for producing cost-effective dry erase presentation boards, schedules, year planners, maps etc.

#### **Product Structure**

Film:	40μ Clear Gloss Polypropylene
Adhesive:	Aqueous Acrylic (Pressure Sensitive)
Release Liner:	1 Side PE Coated Siliconised Kraft Paper

65µ (2.6 mil)

#### **General Properties**

Film Thickness  $40\mu$  (1.6 mil) Adhesive Layer  $25\mu$  (1 mil)

Outdoor Durability n/a

Adhesive contains UV stabilisers, which prevent film degradation and

provides UV protection to the underlying image.

Application Temperature >5°C

Service Temperature Range -20°C to 120°C

Shelf Life Use within 1 year after opening original box.

Storage Conditions 15°C to 22°C; 50 to 55% Relative Humidity

### **Process Settings**

Roller Laminator	Vacuum Press
Temp: Room temp to 40°C (104°F) Speed: 0.3m to 2.5m (1ft to 8ft) per minute	n/a

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to careful quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale.

Drytac Europe Ltd (UK) - Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660 Drytac Corp. (USA) - 5601 Eastport Boulevard, Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610 Drytac Canada Inc. (Canada) - 105 Nuggett Court, Brampton, Ontario L6T 5A9, CA Telephone 001-9056-601-748

http://www.drytac.com October 2015